



Material Datasheet

Recycled Compound



Property	Test Method	Test Conditions	Typical Values	Unit
Melt Flow Index	ISO 1133	2.16kg / 190°C	7	g/10 min
Density	ISO 1133		0.950	g/cm ³
Moisture	INTERNAL		0.08	%
Izod Impact Strength	ISO 180	Notched, 23°C	4.5	KJ/m ²
Flexural Modulus	ISO 178	10mm / min	850	MPa
Ash Content	INTERNAL	400°C / 30 min	3	%

Additional Information	Options
Packaging Types Available	25Kg Bag
	Bulk Bag

Note:

These properties are provided as a guide and should not be construed as binding specification limits or minimum values. This document does not create any liability, warranty or guarantee of product performance. It is the buyer's responsibility to determine the suitability of IIS Polymers products for the intended application